
	Tehničke karakteristike gotove robe TAFTING REZIDENCIJALNI- RASEN ED-04-01-00-862	Izdanje/ Версия/Edition 1 27.11.2018.		Strana/ Страница/ Page 1/3
		Revizija/Ревизия / Revision		



društvo sa ograničenom odgovornošću
21400 Bačka Palanka, Industrijska zona 14, Srbija

Общество с ограниченной ответственностью
21400 БАЧКА ПАЛАНКА, Индустриальная зона 14, СЕРБИЯ



Limited Liability Company
21400 Backa Palanka, Industrijska zona 14, Serbia

ED-04-01-00-862



Tehničke karakteristike gotove robe TAFTING REZIDENCIJALNI- RASEN (Veštačka trava)

**Технические характеристики готовой продукции- Бытовое та
фтинговое покрытие для пола – RASEN (искусственная трава)**

**Technical characteristics of finished products- Tufted
carpets –residential – RASEN (artificial grass)**

Izradio/Создал/Created:	Odobrio/Утвердил/Approved by:	Pregledao i overio/Проверено/ Reviewed and verified by:
Menadžer razvoja, istraživanja i industrijalizacije / Менеджер по развитию, исследованию и индустриализации / R&D and industrialization Manager Lešić Vesna 	Direktor razvoja, istraživanja dizajna i inovacija iz oblasti konstrukcije površine proizvoda/ Директор по развитию, исследованию, дизайну и инновациям на поверхности пола /R&D, design and floor surface innovation director Martinović Dragana 	Predstavnik rukovodstva za IMS Tarkett doo/ Представитель руководства для ИСУ Tarkett doo /Representative of the management for IMS Tarkett doo

KOMERCIJALNI NAZIV PROIZVODA/ Commercial product name / Торговое название продукта	RASEN			
Tehničke karakteristike / Технические характеристики/ Technical characteristics	Deklarisana vrednost/ Объявленная ценность/ Declared value	Odstupanja/ Отклонения/ Tolerances	Jedinica mere/ Единица измерения/ Measuremen t unit	Metoda ispitivanja/ Метод испытания/ Test method
Tip mašine /Тип машины/ Machine type	3/8 cut			
Tip dorade /Тип доработки/ Type of backcoating	Lateks kompaund sa perforacijom/ Латексный компаунд с дренажом/ Latex compaund with drainage holes			
Sastav flora /Сырьевой состав ворса / Pile raw material	55% PE-MF-ravni/ прямой/straight 45% PP-kovrdžavi/ кудрявый/curled		%	ISO 1833
Primarna tkanina /Сырьевой состав первичной основы/ Primary backing	100 % PP – tkanina/ткань/woven		%	ISO 1833
Vezivno sredstvo / Приклею/ Finishing agent for back coating	Lateks kompaund/подоснова латекс/Latex compaund		%	
Masa flora/ Вес ворса/ Pile weight	650	(+15% /-10%)	g/m ²	ISO 8543
Konstrukcija flora/Вид ворса/ Pile type	Sečena petlja/ разрезная петля/ cut pile			
Ukupna masa/ Плотность / Total weight	1.350	(±15%)	g/m ²	ISO 8543
Visina flora/ Высота ворса/ Pile height	17,0	(+15% /-10%)	mm	ISO 2549
Ukupna debljina poda / Толщина покрытия /Total thickness	-	(+15% /-10%)	mm	ISO 1765
Broj čvorova /Количество петель/ Number of tufts or loops	12.598	(+10% /-7,5%)	Čv./шт./No./m 2	ISO 1763
Jačina petlje na izvlačenje/ Сила вывода петли/Tuft withdrawal force	Min. 20	Min. 20	N	ISO 4919
UV stabilnost/UV Stability	>5000 h UV-A			ISO 11507-A
Postojanost boje -Otpornost na morsku vodu/ Цветоустойчивость к морской воде /Colour fastness to sea water	4/5	Min. 4		EN ISO 105-E02
Postojanost boje-otpornost na hlorisanu vodu/ Устойчивость цвета к хлорированной воде/ Colour fastness to chlorinated water	5	Min. 4		DIN EN 105-E03
Postojanost boje na svetlo/ Светоустойчивость/Light fastness	8	Min. 5	Plava skala (Серая шкала/ Blue Scale)	ISO 105-B02
Komfortabilnost/ Класс люкс/ Luxury class	LC2			EN 1307
Upotreba/использование /usage	Spoljašnja/ внешнее/Outdoor			

	Tehničke karakteristike gotove robe TAFTING REZIDENCIJALNI-RASEN ED-04-01-00-862	Izdanje/ Версия/Edition 1 27.11.2018.		Strana/ Страница/ Page 3/3
		Revizija/Ревизија / Revision		

